

Issue 3

## **DATA SHEET**

## MATERIAL REFERENCE - FLUORINOID® FL 103

DESCRIPTION GLASS FIBRE FILLED PTFE

FORMULATION 85% PTFE, 15% GLASS FIBRE (BY WEIGHT)

## **TYPICAL APPLICATIONS**

Glass fibre is the most commonly used filler for sealing applications. It gives improved compression and wear properties.

This material may be inert gas sintered to further improve creep properties and reduce porosity and gas permeability. There will be a consequent loss of tensile properties.

## TYPICAL PHYSICAL PROPERTIES #

SPECIFIC GRAVITY (BS EN ISO 13000-2) 2.20 – 2.25

TENSILE STRENGTH (BS EN ISO 13000-2) min. 18.0 MPa

ELONGATION (BS EN ISO 13000-2) min. 225 %

SHORE D HARDNESS (BS EN ISO 13000-2) 60 - 70

Quality control of 15% glass fibre filled PTFE is covered by BS 6564: Part 3

# These figures are typical values for the material and do not represent a product specification. Properties will vary depending on the source of raw material, method of processing, physical form of the product, direction of measurement etc.

Fluorocarbon Headquarter Unit C Argyle Gate, Argyle Way Stevenage, Hertfordshire SG1 2AD, UK

Tel: +44 (0)1992 550731
Fax: +44 (0)1992 584697
Email: info@fluorocarbon.co.uk
Web: www.fluorocarbon.co.uk