

PRODUCT DATA SHEET F-LON® 5030 Series

F-LON® 5030 is an excellent **Low Friction** coating for use on temperature sensitive substrates.

F-LON® 5030 is a patented fluoropolymer coating, which is normally applied in a single coat, exhibiting the following properties:

- Good flexibility.
- Low core temperatures.
- Excellent weather resistance.
- Excellent adhesion to most substrates.
- Low coefficient of friction.

F-LON® 5030 was developed for applications which:

- Need protection against environmental attack.
- Must operate on flexible substrates.

Chemical composition: Blend of resins, pigments & fluoropolymer resins in industrial organic solvents.

F-LON® 5030 Series

Recommended Dry Film Thickness	8-25µ
Substrates	Rubber substrates eg. EPDM, VITON.
Pre-treatment	Light degrease.
Application method	Hand spray or automatic spray line.
Curing schedule	Optimum cure 15 minutes @ 150°C Maximum cure 5 minutes @ 180°C Minimum cure 30 minutes @120°C
Operating Temperature	-20 to + 150 °C
Colours available	Black
Typical applications	Rubber Seals, Extrusions & Rubber Gaskets.
Other properties	Corrosion resistance Non stick Weather resistance Low cure

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon Group Limited

