

MATERIAL DATASHEET

Material Reference:
FLUORONOID® FL105
Glass Fibre Filled PTFE

+44 (0) 845 2505 100 
info@fluorocarbon.co.uk 
www.fluorocarbon.co.uk 

> Description >

Glass fibre is the most commonly used filler for sealing applications. It gives improved compression and wear properties.

This material may be inert gas sintered to further improve creep properties and reduce porosity and gas permeability. There will be a consequent loss of tensile properties.

> Typical Physical Properties

| Properties | Value | Method |
|-----------------------|-----------------|-------------|
| Specific Gravity | 219-229 | BSN 13000-2 |
| Tensile Strength | min. 15.7 MPa | BSN 13000-2 |
| Elongation | min. 200% | BSN 13000-2 |
| Shore D Hardness | 57-65 | BSN 13000-2 |
| Continuous Temp Range | -260°C to 260°C | |

These figures are typical values for the material and do not represent a product specification. Properties will vary depending on the source of raw material, method of processing, physical form of the product, direction of measurement etc.